

Diamante

Description	Silane-terminated binder based on α -silane technology INTERIOR
Support surface	Traditional or pre-mixed plaster, gypsum boards
Composition	α -silane-terminated polyethers
Technical Characteristics	
Specific Weight	1,15 \pm 0,02 Kg/L
Yield	14-16 m ² /L for each coat
Dry to touch	24 h at 20 °C RU 60%
Application	
Environmental conditions	T. min 5 °C T.max 30 °C R.U. 60%
Tools	Brush or Sponge Roll
Dilution	Mix component B in component A (5:100)
Pot Life	300 days
Colours	Transparent
Advices	Always apply in the recommended condition. Verify the support status before beginning and check that the surfaces is clean, dry and with uniform absorption. One coat of Protettivo Trasparente FDA before the application of Diamante is required.

Component B should be placed directly into container Component A, mix the two components avoid bubbles. Apply a first coat of the product using a brush or a sponge roll. After 24 hours apply a second coat in the same way in order to obtain a more uniform surface. The product, once the two component are mixed, was used no later than 10 mounts.

Packaging:

Diamante Componente A: 1,0 Lt

Diamante Componente B: 50 mL

Storage: Minimum Temperature: 5 °C

Maximum Temperature: 30 °C

Waste treatment methods:

Empty Can: special waste similar to urban waste

Can with residue: special waste

Stability:

360 days in the original cans.

F.D.A. s.r.l.

24043 Caravaggio / BG

Via Piave,1

Tel. e Fax +39 035 578 51 39 info@firmadautore.it

The above technical information is the result of accurate laboratory tests and practical experience. However, given that the product is often used without our control, we cannot but guarantee its quality. This information is subject to possible updates by the company.