

Marmorino Medio

Description	Decorative product based on slaked lime INTERIOR
Support surface	Traditional or pre-mixed plaster, gypsum boards
Composition	Water dispersion based on organic binder and slaked lime
Technical Characteristics	
Specific Weight	1,7 ± 0,02 Kg/L
pH	<12
Yield	0,6/0,8 m ² /Kg for each coat
Dry to touch	10-12 h at 20 °C RU 60%
Application	
Environmental conditions	T. min 5 °C T.max 30 °C R.U. 65%
Tools	INOX Spatula and sponge float
Dilution	Ready to Use
Colours	White, Colour chart Calce Firma d'Autore
Advices	Always apply in the recommended condition. Verify the support status before beginning and check that the surfaces is clean, dry and with uniform absorption. Before apply one coat of Fondo FDA Medio.

Spread the first coat of Marmorino Medio using Spatula INOX, leave a thick layer of material suitable for the grain of the product, avoiding scratches. Allow to dry for at least 8 hours and then apply a second coat in the same way. As soon as the application is completed, go over the surface again with the sponge float using circular strokes. Avoid applying in full sun and in presence of wind. Any precipitation that occurs within the first week of product maturation could result in stains on the wall due to rain

Packaging:

Marmorino Medio: 20 Kg and 8 Kg

Waste treatment methods:

Empty Can: special waste similar to urban waste

Can with residue: special waste

Storage: Minimum Temperature: 5 °C

Maximum Temperature: 30 °C

Stability:

360 days in the original cans.

F.D.A. s.r.l.

24043 Caravaggio / BG

Via Piave,1

Tel. e Fax +39 035 578 51 39 info@firmadautore.it

The above technical information is the result of accurate laboratory tests and practical experience. However, given that the product is often used without our control, we cannot but guarantee its quality. This information is subject to possible updates by the company.