

# Marmorino Medio

|                                  |  |
|----------------------------------|--|
| Description                      | Decorative product based on slaked lime<br>INTERIOR  |
| Support surface                  | Traditional or pre-mixed plaster, gypsum boards  |
| Composition                      | Water dispersion based on organic binder and slaked lime   |
| <b>Technical Characteristics</b> |  |
| Specific Weight                  | 1,7 ± 0,02 Kg/L  |
| pH                               | <12  |
| Yield                            | 1,0/1,2 m <sup>2</sup> /Kg for each coat   |
| Dry to touch                     | 10-12 h at 20 °C RU 60%  |
| <b>Application</b>               |  |
| Environmental conditions         | T. min 5 °C T.max 30 °C R.U. 65%   |
| Tools                            | INOX Spatula and sponge float  |
| Dilution                         | Ready to Use   |
| Colours                          | White, Colour chart Calce Firma d'Autore   |
| Advices                          | Always apply in the recommended condition. Verify the support status before beginning and check that the surfaces is clean, dry and with uniform absorption. Before apply one coat of Fondo FDA Medio. |

Spread the first coat of Marmorino Medio using Spatula INOX, leave a thick layer of material suitable for the grain of the product, avoiding scratches. Allow to dry for at least 8 hours and then apply a second coat in the same way. As soon as the application is completed, go over the surface again with the sponge float using circular strokes. Avoid applying in full sun and in presence of wind. Any precipitation that occurs within the first week of product maturation could result in stains on the wall due to rain

**Packaging:**

Marmorino Medio: 20 Kg and 8 Kg

**Waste treatment methods:**

Empty Can: special waste similar to urban waste

Can with residue: special waste

**Storage:** Minimum Temperature: 5 °C

Maximum Temperature: 30 °C

**Stability:**

360 days in the original cans.

**F.D.A. s.r.l.**

24043 Caravaggio / BG

Via Piave,1

Tel. e Fax +39 035 578 51 39 [info@firmadautore.it](mailto:info@firmadautore.it)

The above technical information is the result of accurate laboratory tests and practical experience. However, given that the product is often used without our control, we cannot but guarantee its quality. This information is subject to possible updates by the company.