

# Ruggine FDA

Description	Micaceous finishes with rust effect INTERIOR
Support surface	Traditional or pre-mixed plaster, gypsum boards
Composition	Water dispersion with organic binder
<b>Technical Characteristics</b>	
Specific Weight	1,4 ± 0,03 Kg/L
pH	8,5
Yield	8/9 m <sup>2</sup> /L for each coat
Dry to touch	2-3 h at 20 °C RU 60%
<b>Application</b>	
Environmental conditions	T. min 5 °C T.max 30 °C R.U. 60%
Tools	Brush and INOX Spatula
Dilution	Ready to Use
Colours	Rust
Advices	Always apply in the recommended condition. Verify the support status before beginning and check that the surfaces is clean, dry and with uniform absorption. Before apply one coat of Fondo Metallico FDA.

## APPLICATION FERRO EFFETTO RUGGINE:

On the surface previously treated with Fondo FDA Fine, spread a coat of Fondo Metallico FDA using a brush, taking care to distribute the product not in a uniform way, creating areas with more product that determine the final decorative effect. When Fondo Metallico FDA is completely dry (after 4-5 hours) apply on the surface, using a brush, Ruggine FDA. Distribute the product with a steel, taking care to highlight the areas with more Fondo Metallico FDA. A second coat of Ruggine FDA may be applied depending on the desired effect.

### Packaging:

Ruggine FDA: 2,5 Lt and 1,0 Lt

### Stability:

360 days in the original cans.

### Waste treatment methods:

Empty Can: special waste similar to urban waste  
Can with residue: special waste

**Storage:** Minimum Temperature: 5 °C

Maximum Temperature: 30 °C