

Stucco a Calce

Description	Finishing product based on slaked lime for spatolato Veneziano effect INTERIOR
Support surface	Traditional or pre-mixed plaster, gypsum boards
Composition	Water dispersion based on organic binder and slaked lime
Technical Characteristics	
Specific Weight	1,5 ± 0,02 Kg/L
pH	<12
Yield	2,5/3,0 m ² /Kg for each coat
Dry to touch	10-12 h at 20 °C RU 60%
Application	
Environmental conditions	T. min 5 °C T.max 30 °C R.U. 65%
Tools	INOX Spatula or Plastic Trowel
Dilution	Ready to use
Colours	WHITE, color chart Calce Firma d'Autore
Advices	Always apply in the recommended condition. Verify the support status before beginning and check that the surfaces is clean, dry and with uniform absorption. Before apply one coat of Fondo FDA Fine or apply on Calce Iulia.

APPLICATION Stucco a Calce:

Spread a first coat of colored Stucco a Calce, using INOX spatula filling in and leveling in order to provide an even surface, allow to harden for at least 12 hours. Apply a second coat of the product in random, small clumps and then smooth over using INOX spatula avoiding excessive accumulations. Depending on the desired effect, a third coat may be applied after 12 hours, with irregular strokes using INOX spatula filling in and leveling in order to provide an even surface. After 5-6 hours of applying the final coat, polish the surface with a clean, unflawed INOX spatula.

"Cera d'Api" (bee's wax) can be applied on the finish after at least 48 hours by rubbing a thin layer of over the whole surface using a sponge, until it is completely absorbed avoiding excessive accumulations of material. After 5/10 minutes proceed with polishing using a non-abrasive soft cloth (microfiber, cotton or linen).

APPLICATION Finitura Iulia:

On the surface previously treated with Fondo FDA medio, spread a coat of white Calce Iulia FDA using a stainless steel spatula applying a homogeneous coat on the whole surface, then finish with Sponge Float in circular movements. Leave for 12 hours then spread a first coat of Stucco a Calce in the chosen colour using a stainless steel spatula, in such a way to enhances the surface irregularities. After 12 hours apply a second coat of the product in random, small clumps and then smooth over using a INOX spatula avoiding excessive accumulations. After 5-6 hours of applying the final coat, polish the surface with a clean, unflawed stainless steel spatula. The amount of material used and the spatula stroke dimension, shape and intensity all determine the personalized decorative effect achieved.

"Cera d'Api" (bee's wax) can be applied on the finish after at least 48 hours by rubbing a thin layer of over the whole surface using a sponge, until it is completely absorbed avoiding excessive accumulations of material. After 5/10 minutes proceed with polishing using a non-abrasive soft cloth (microfiber, cotton or linen).

APPLICATION CERE D'AUTORE:

F.D.A. s.r.l.
24043 Caravaggio / BG
Via Piave,1
Tel. e Fax +39 035 578 51 39 info@firmadautore.it

The above technical information is the result of accurate laboratory tests and practical experience. However, given that the product is often used without our control, we cannot but guarantee its quality. This information is subject to possible updates by the company.

Spread a first coat of white or colored Stucco a Calce, using a plastic spatula filling in and leveling in order to provide an even surface, allow to harden for at least 12 hours.. Apply a second coat of the product in random, small clumps and then smooth over using a plastic spatula avoiding excessive accumulations. Depending on the desired effect, a third coat may be applied after 12 hours, with irregular strokes using a plastic spatula filling in and leveling in order to provide an even surface. After 5-6 hours of applying the final coat, polish the surface with a clean, unflawed plastic spatula. After at least 24 hours of polishing, apply Cera by rubbing a thin layer of Cera, in the chosen colour, over the whole surface using a sponge, until it is completely absorbed avoiding excessive accumulations of material. After 5/10 minutes proceed with polishing using a non-abrasive soft cloth (microfiber, cotton or linen) . The waiting times of the polishing of the Stucco a Calce and the application of Cera, the chosen colour and the application of Stucco a Calce all determine the personalized decorative effect achieved.

Packaging:

Stucco a calce: 20 Kg, 8 Kg and 2 Kg

Waste treatment methods:

Empty Can: special waste similar to urban waste

Can with residue: special waste

Storage: Minimum Temperature: 5 °C

Maximum Temperature: 30 °C

Stability:

360 days in the original cans.

F.D.A. s.r.l.

24043 Caravaggio / BG

Via Piave,1

Tel. e Fax +39 035 578 51 39 info@firmadautore.it

The above technical information is the result of accurate laboratory tests and practical experience. However, given that the product is often used without our control, we cannot but guarantee its quality. This information is subject to possible updates by the company.